

# MILES #8648 Ambient Powder Strip - Thin

## T E C H N I C A L   D A T A   S H E E T

---

**Description:** #8648 is a paint strip solution formulated to undercut and remove cured Powder Coating from Aluminum and Steel substrates. #8648 can be used to strip E-coat racks and paint rework when HEATED.

**Directions:** Utilize an immersion strip tank with proper ventilation. Immerse Powder Coated parts & hooks in heated-#8648 at 50% concentration with water or (100%- neat at Ambient Temperatures for 1-hour to overnight). For (E-coat removal, utilize #8648 heated only) at 50% concentration with water at temperatures of 150F.-185F. Strip time is 10 minutes to 45 minutes.

**Warning:** May be harmful if swallowed. May cause skin and eye irritation. Eye protection and rubber gloves are recommended when handling this product.

**First Aid:** In case of eye or skin contact flush with large amounts of water for 15 minutes. If irritation persists, see physician. In case of ingestion, do not induce vomiting; drink large quantities of water to dilute product. Get medical attention at once.

**Hazard Class:** (Contains Glycolic Acid), 8, UN1760

<b>Properties:</b>	pH:	N/AP - N/AP	Health:	2
	Specific Gravity:	1.04 - 1.06	Flammability:	0
	Color:	Clear to Milky	Reactivity:	0